



RAPIDSHINE

Application and Specifications

Application

- Nasiol Quick ceramic coating has been developed for both end users and professionals. Application to a mid-size car takes 20-25 minutes. Ensure that the temperature and relative humidity (RH) values (+5 °C ~ +45 °C / 41 °F ~ 113 °F / 50% RH) of the application space are as close as possible to suggested condition in order to obtain maximum product performance.
- Avoid direct sunlight during the application and only work on cool surfaces.
- Prepare the surface by applying Nasiol® Clean to remove any residual contamination and dry with a clean, lint-free microfiber cloth prior to the use of product.
- Do not work on an area larger than 2 m² at a time.
- Shake the product gently before use.

Specifications

Packaging	500 mL
Appearance	Milky liquid
Durability	1 year
Pencil Hardness (ISO-15184:2012)	NA
Dry Film Thickness	700-800 nm
Consumption per Unit Area	8-10 mL/m ²
Density @23°C	0,99
pH Value	7-7,5
Dry to Touch Time	2h
Application Temperature	5°C-45°C (≤50%RH)
Temperature Durability	NA
Water Contact Angle	102.7°
Water Sliding Angle	18°