



# HOMESHINE

## Application and Specifications

### Application

Surfaces should be dry and free of any dust, wax, oil, grease and other contamination. Product is sprayed approximately 10 times onto a 0.5 m<sup>2</sup> area. The surface should be buffed immediately with a dry cotton cloth. Wait for 24 hours for drying and curing period.

### Specifications

Volume	150 ml
Application surface type	Home glass and ceramic
Durability	1 year
Temperature durability	275°C
Chemical resistance	13>pH>1
Consumption	5-6 ml/m <sup>2</sup>
Coating thickness	85-100 nm
Water repellency	√
Oil repellency	√
Line stains	Reducing %90
Shelf life	2 years
Keeping conditions	-3°C to +30°C
Curing period	24 h