



MARINECOAT FAST

Application and Specifications

Application

Surfaces should be dry and free of any dust, wax, oil, grease and other contamination. Ensure that the temperature and relative humidity (RH) values (+5°C ~ + 30°C / 41°F ~ 86°F /50% RH). Wear the protective nitrile gloves. Shake product gently before use. Spray on one square meter around 20-30

times with a standard MarineCoat Fast bottle (5-8 mL/m²) and buff immediately with Nasiol Microfiber Cloth. Keep the coated surfaces away from direct sunlight, the elements, various types of contamination, and water exposure for 24 hours.

Specifications

Packaging	200 mL
Appearance	Colorless liquid
Durability	Up to 1 season
Chemical Resistance	12>pH>1
Salt Water Resistance	Yes
Moisture Resistance	Yes
Pencil Hardness (ISO-15184:2012)	7H
Dry Film Thickness	200-300 nm
Consumption per Unit Area	5-8 mL/m ²
Density @23°C	0.8 g/cm ³
pH Value	4.8-5
Dry to Touch Time	4h
Application Temperature	5°C-30°C (≤50%RH)
Temperature Durability	275°C
Water Contact Angle	97° @10 μL
Water Contact Angle After "3000 Wet Scrub (ISO-11998:2006)	93° @10 μL
Water Sliding Angle	23° @20 μL
Oil Contact Angle	76° @10 μL
Gloss Rate @60° (ISO-2813:2014)	93 (Acrylic)
Volatile Organic Compound (VOC) (ASTM D-2369)	733 g/L (91.6%)
REACH Compliance	Yes