



DECKCOAT

Application and Specifications

Application

Surfaces should be dry and free of any dust, wax, oil, grease, and other contamination. Avoid direct sunlight during the application and only work on cool surfaces. The product may not work on insufficiently cleaned surfaces. Ventilate the application area well. Shake the product gently

before use. Consumption is 40-60 mL/m². Spray on one square meter around 140-200 times with the standard DeckCoat bottle until the surfaces becomes wet. Wait for 24 hours for drying and curing. The effect of the product can change with respect to wooden type.

Specifications

Packaging	500 mL
Appearance	Colorless Liquid
Durability	Up to 1 season
Chemical Resistance	11>pH>1
Dry Film Thickness	60-70 nm
Consumption per Unit Area	40-60 mL/m ²
Density @23°C	0.809 g/cm ³
pH Value	2.0
Breathability	Yes
Application Temperature	5°C-30°C (≤50% RH)
Temperature Durability	110°C
Water Contact Angle	144° @10 μL
Water Sliding Angle	16° @20 μL
Oil Contact Angle	90° @10 μL
REACH Compliance	Yes