



LEATHERCOAT

Application and Specifications

Application

Surfaces should be dry and free of any dust, wax, oil, grease and other contamination. Consumption amount is 35-45 mL/m² for genuine leather and 30-40 mL/m² for artificial leather. Do not use it excessively. Gently shake the product bottle before use.

Pour the product from the standard Nasiol LeatherCoat Marine bottle onto the applicator cloth placed on the applicator block and spread it homogeneously with

horizontal and vertical movement to the surface. Make sure that there are no dry areas. Wait for 24 hours for drying and curing period. Throughout the curing time, keep the coated surface away from direct sunlight, excessive dust, water, and other contaminants. In case of an accidental application to surfaces other than the specified ones, the surface should be wiped off immediately with a clean and lint-free microfiber cloth.

Specifications

Packaging	150mL
Durability	Up to 1 Year
Chemical Resistance	11>pH>2
Salt Water Resistance	Yes
Moisture Resistance	Yes
Dry Film Thickness	700-1000 nm
Density @23°C	0.86 g/cm ³
pH Value	5-5.5
Application Temperature	5°C-30°C (≤50% RH)
Temperature Durability	150°C
Water Contact Angle	135° @10 μL
Water Contact Angle After "2000 Wet Scrub (ISO-11998:2006)	117° @10 μL
Water Sliding Angle	18° @20 μL
Oil Contact Angle	105° @10 μL
Dry-to-Touch Time	2h
REACH Compliance	Yes